

# MULTIBOARD® | Offset

Grammage	g/m <sup>2</sup>	280	300	325	350	375	400	425	450
Thickness	μm	375	405	445	480	515	550	585	630
Bending resistance L & W 15°, mN	MD	275	335	420	515	620	745	890	1050
	CD	100	120	150	185	225	270	310	370
Bending stiffness DIN 5°, mNm	MD	24,5	30,0	37,9	46,7	56,5	68,2	82,2	97,8
	CD	9,7	11,6	14,6	17,9	21,8	26,2	30,1	35,9
Bending moment Taber 15°, mNm	MD	13,3	16,2	20,3	24,9	29,9	36,0	43,0	50,7
	CD	4,8	5,8	7,2	8,9	10,9	13,0	15,0	17,9

**Brightness** ISO (R457) % 79  
**Whiteness** ISO (D65/10) % 84  
**Test climate** 50% RH/23° C  
**Tolerances based upon 95 % confidence limits.**  
 Grammage +/- 3 %  
 Thickness +/- 5 %  
 Bending resistance - 15 %  
 Brightness min 78 %

**Bending resistance is measured. Bending stiffness and bending moment are calculated from measured bending resistance. Test methods:**

Grammage ISO 536  
 Thickness ISO 534  
 Bending resistance ISO 2493  
 Bending moment Tappi 489  
 Bending stiffness DIN 53121  
 Brightness (R457) ISO 2470  
 Whiteness ISO (D65/10) ISO 11475

Confirmed January 2024. This specification can be changed without notification.

